

# UVivid

UV Narrow Web Printing Inks

## UVivid RVA07 UV Flexo Primer

### Features

- Excellent adhesion to metallised PET films
- Optimum overprint adhesion with UVivid ink systems
- Easy to use

UVivid RVA07 UV Flexo Primer is a high performance UV Flexo primer designed to promote the adhesion of UVivid UV flexo ink systems on to metallised PET films.

### Application

UVivid RVA07 UV Flexo Primer is suitable for a range of applications including self-adhesive labels, sachets and pouches.

Anilox	Print Speed	Lamp Power*
3.5 - 8 cm <sup>3</sup> /m <sup>2</sup>	Up to 50m/min	160w/cm (400w/inch) bulb 100% power

\*Based on prints from a Nilpeter FA2500 press

**Note:** Optimum adhesion is often obtained by printing low film weights.

### Additives

Thinning of RVA07 is not recommended.

RVA07 must only be used as a primer, under no circumstances should it be added to inks. Additives should not be used in RVA07 without checking with Sericol's Technical Service Department.

### Wash-up

Application	Product	Code	Pack size
To clean plates, rollers and other equipment	General Cleaner	DFGC1	5lt
To remove deep-seated ink deposits from anilox rollers	Appollo Deep Clean	DFDCL	1lt
For use in automatic solvent washout units	Autowash Cleaner	DFAUT	15lt

### Pre-production testing

UVivid Flexo RVA07 Flexo Primer is formulated to adhere to most major brand metallised PET films. However, it is strongly recommended that all substrates be tested before use in a commercial situation. Similar substrates can vary between manufacturers, and between batches from the same manufacturer. Certain synthetics may be impregnated with lubricants, which may migrate and may impair adhesion.

It is also recommended to thoroughly test the combination of RVA07 Flexo Primer and UVivid Flexo ink systems under production conditions.

**The end-user must determine suitability of this product for the intended use prior to production.**

### Storage

Containers should be tightly closed immediately after use. At the end of long print runs surplus primer from the duct should be disposed of. Uncontaminated press returns should be stored under the same conditions as unopened containers. These returns should be used within 3 months of the original date of manufacture. UVivid RVA07 UV Flexo Primer should not be stored in direct sunlight or near warm pipes and should be kept away from Peroxides. In the interest of maximum shelf-life storage temperatures should be between 10°C and 25°C. Inks and additives should not be stored in direct sunlight or extreme temperatures. Refer to Material Safety Data Sheet (MSDS) for materials and conditions to be avoided.

### Shelf-life

When stored unopened in a cool environment UVivid RVA07 UV Flexo Primer is expected to have a shelf-life of approximately 12 months from the original date of manufacture.

**SERICOL**  
More than ink... Solutions.

 FUJIFILM

## Pack Size

UVivid RVA07 UV Flexo Primer is available in a 5 kg pack size.

## Fujifilm Sericol UK Limited

- Has certification to the International Environmental Standard, ISO 14001.
- Is committed to minimising the risk to users of our products, and also to minimising the impact of our activities on the environment, from formulation through to production and supply.
- Research & development team, work to an in house Health, Safety and Environmental policy, termed 'Design for Health, Safety and Environment', with the aim of proactively developing products with the least impact on health, safety and the environment.
- Regularly review and monitor our impacts and activities, setting objectives and targets as part of a continual improvement process.
- Is committed to reducing waste through better use of raw materials, energy, water, re-use and recycling.

## Safety and Handling

UVivid RVA07 UV Flexo Primer:

- Is formulated to be free from any chemicals toxic to health, carcinogenic, mutagenic or reprotoxic according to Directive 67/548/EC.
- Has a flashpoint greater than 55°C and is therefore not classified as a 'dangerous substance' under the Dangerous Substances and Explosive Atmospheres Regulations (DSEAR).
- Comprehensive information on the safety and handling of UVivid RVA07 UV Flexo Primer and associated products is given in the appropriate Sericol Safety Data Sheet.

## Environmental

UVivid RVA07 UV Flexo Primer:

- Does not contain ozone depleting chemicals as described in the Montreal Convention.
- Is formulated free from aromatic hydrocarbons.
- Is not routinely tested, but is formulated to comply with the EN71-3 1995 Toy Safety Standard.

*The information and recommendations contained in this Product Information sheet, as well as technical advice otherwise given by representatives of our Company, whether verbally or in writing, are based on our present knowledge and believed to be accurate. However, no guarantee regarding their accuracy is given as we cannot cover or anticipate every possible application of our products and because manufacturing methods, printing stocks and other materials vary. For the same reason our products are sold without warranty and on condition that users shall make their own tests to satisfy themselves that they will meet fully their particular requirements. Our policy of continuous product improvement might make some of the information contained in this Product Information sheet out of date and users are requested to ensure that they follow current recommendations.*

**SERICOL**  
More than ink...Solutions.



**FUJIFILM**

FUJIFILM SERICOL UK LIMITED

Pysons Road Broadstairs Kent CT10 2LE United Kingdom  
Tel: (01843) 866668 Fax: (01843) 872184



**UK Sales** Tel: (01992) 782619 Fax: (01992) 782602  
Email: UKsales@fujifilmsericol.com

**Customer Service Centres** Tel: 0845 084 89 89

**Technical Helpline** Tel: 0845 770 80 70

**Export Sales**

Pysons Road Broadstairs Kent CT10 2LE United Kingdom  
Tel: +44 (0)1843 866668 Fax: +44 (0)1843 872122  
Email: Exportsales@fujifilmsericol.com

[www.fujifilmsericol.com](http://www.fujifilmsericol.com)