

UVivid

UV Narrow Web Printing Inks

UVivid RVA15

UV Flexo Laminating Adhesive

Features

- Good adhesive properties
- High reactivity
- Low viscosity
- Good adhesion

Application

UVivid RVA15 UV Laminating Adhesive is a high performance low viscosity UV adhesive suitable for the lamination of OPP films on to coated papers and treated or primed polyethylene and polypropylene.

Printing Recommendations

| Anilox | Print Speed | Lamp Power* |
|----------------------------|---------------|-------------------------------------|
| 120-160 l/cm 300-400lpi | Up to 80m/min | 160w/cm (400w/inch) bulb 100% power |

*Based on prints from a Nilpeter FA2500 press

Wash-up

| Application | Product Reference | Product Code |
|---|-------------------|--------------|
| To clean plates, rollers and other equipment. | General Cleaner | DFGC1 |
| To remove deep-seated ink deposits from anilox rollers. | Apollo Deep Clean | DFDCL |
| For use in automatic solvent washout units. | Autowash Cleaner | DFAUT |

Pre-production testing

UVivid Flexo RVA15 UV Laminating Adhesive is formulated to adhere to most major manufacturers coated papers and treated or primed polyethylene and polypropylene. However, it is strongly recommended that all substrates be tested before use in a commercial situation. Similar substrates can vary between manufacturers, and between batches from the same manufacturer. Certain synthetics may be impregnated with lubricants, which may migrate and may impair adhesion.

The end-user must determine suitability of this product for the intended use prior to production.

Storage

Containers should be tightly closed immediately after use. At the end of long print runs surplus adhesive from the duct should be disposed of. Uncontaminated press returns should be stored under the same conditions as the unopened containers. These returns should be used within 3 months of the original date of manufacture. UVivid Flexo RVA15 UV Laminating Adhesive should not be stored in direct sunlight or near warm pipes and should be kept away from Peroxides. In the interest of maximum shelf-life storage temperatures should be between 10°C and 25°C. Inks and additives should not be stored in direct sunlight or extreme temperatures. Refer to Material Safety Data Sheet (MSDS) for materials and conditions to be avoided.

Shelf-life

When stored unopened in a cool environment all UVivid Flexo RVA15 UV Laminating Adhesive is expected to have a shelf life of approximately 6 months from the original date of manufacture.

Pack Size

UVivid Flexo RVA15 UV Laminating Adhesive is available in a 5kg pack size.

SERICOL
More than ink... Solutions.

 FUJIFILM

Fujifilm Sericol UK Limited

- Has certification to the International Environmental Standard, ISO 14001.
- Is committed to minimising the risk to users of our products, and also to minimising the impact of our activities on the environment, from formulation through to production and supply.
- Research & development team, work to an in house Health, Safety and Environmental policy, termed 'Design for Health, Safety and Environment', with the aim of proactively developing products with the least impact on health, safety and the environment.
- Regularly review and monitor our impacts and activities, setting objectives and targets as part of a continual improvement process.
- Is committed to reducing waste through better use of raw materials, energy, water, re-use and recycling.

Safety and Handling

UVivid Flexo RVA15 UV Laminating Adhesive:

- Is formulated to be free from any chemicals toxic to health, carcinogenic, mutagenic or reprotoxic according to Directive 67/548/EC.
- Has a flashpoint greater than 55°C and is therefore not classified as a "dangerous substance" under the Dangerous Substances and Explosive Atmospheres Regulations (DSEAR).
- Comprehensive information on the safety and handling of UVivid Flexo RVA15 UV Laminating Adhesive and associated products is given in the appropriate Sericol Safety Data Sheet available upon request.

Environmental Information

UVivid Flexo RVA15 UV Laminating Adhesive:

- Does not contain ozone depleting chemicals as described in the Montreal Convention.
- Is formulated free from aromatic hydrocarbons.
- Is free of any volatile solvent and can therefore be considered to have less impact on the environment, when compared with solvent-based products.

The information and recommendations contained in this Product Information Sheet, as well as technical advice otherwise given by representatives of our Company, whether verbally or in writing, are based on our present knowledge and believed to be accurate. However, no guarantee regarding their accuracy is given as we cannot cover or anticipate every possible application of our products and because manufacturing methods, printing stocks and other materials vary. For the same reason our products are sold without warranty and on condition that users shall make their own tests to satisfy themselves that they will meet fully their particular requirements. Our policy of continuous product improvement might make some of the information contained in this Product Information Sheet out of date and users are requested to ensure that they follow current recommendations.

SERICOL
More than ink... Solutions.



FUJIFILM

FUJIFILM SERICOL UK LIMITED

Pysons Road Broadstairs Kent CT10 2LE United Kingdom
Tel: (01843) 866668 Fax: (01843) 872184



UK Sales Tel: (01992) 782619 Fax: (01992) 782602
Email: UKsales@fujifilmsericol.com

Customer Service Centres Tel: 0845 084 89 89

Technical Helpline Tel: 0845 770 80 70

Export Sales
Pysons Road Broadstairs Kent CT10 2LE United Kingdom
Tel: +44 (0)1843 866668 Fax: +44 (0)1843 872122
Email: Exportsales@fujifilmsericol.com

www.fujifilmsericol.com